

WMP-VR-R PLUS

POLYPROPYLENE / SCRIM / POLYESTER

Meets ASTM C1136, Type II, IV

FACING COMPOSITION	DESCRIPTION	VALUES (ENGLISH)	VALUES (METRIC)
White Film	Polypropylene	0.0015 inch	38.1 micron
Adhesive	Flame Resistant		
Reinforcing	Tri-directional Fiberglass	4 / inch (MD) 4 / inch (XD)	16 / 100 mm (MD) 16 / 100 mm (XD)
Film	Metallized Polyester	0.0005 inch	12.7 micron

PHYSICAL PROPERTIES	TEST METHOD	VALUES (ENGLISH)	VALUES (METRIC)
Basis Weight	Scale	14 lbs / 1000 ft ²	68 g / m ²
Permeance (WVTR)	ASTM E96 Procedure A	0.02 perm (grains/hr'ft ² in Hg)	1.15 ng / N's
Bursting Strength	ASTM D774	100 psi	7.0 kg / cm ²
Tensile Strength	ASTM C1136	35 lbs/inch width (MD) 35 lbs/inch width (XD)	6.1 kN / m (MD) 6.1 kN / m (XD)
Caliper / Thickness	Micrometer	0.007 inch	178 micron
Accelerated Aging	30 Days @ 95% RH, 120°F (49°C)	No Corrosion No Delamination	No Corrosion No Delamination
Low Temperature Resistance	ASTM D1790 -40°F (-40°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
High Temperature Resistance	4 hours @ 240°F (116°C)	Remains Flexible No Delamination	Remains Flexible No Delamination
Water Immersion	24 hours @ 73°F (23°C)	No Delamination	No Delamination
Mold Resistance	ASTM C665 / C1338	No Growth	No Growth
Dimensional Stability	ASTM D1204	0.25%	0.25%
Light Reflectance	ASTM C523	85%	85%

FIRE TESTING	UL-723 / ASTM E84	
	Flame Spread	Smoke Developed
Polypropylene Exposed	10	35
Polyester Exposed	10	40

Physical Properties based upon statistical averages, Weight / Thickness +/- 10%

“LAMTEC” AND “WMP” ARE REGISTERED TRADEMARKS OF LAMTEC CORPORATION

Lamtec Corporation Bartley-Chester Road P.O. Box 37 Flanders, New Jersey 07836-0037 USA

Phone: (973) 584-5500
(800) 852-6832

www.lamtec.com

Fax: (973) 584-5178
(888) 852-6832